

PM-FM transition in a DE model

Eugene Kogan ^a, Mark Auslender ^{b,*}

^a*Jack and Pearl Resnick Institute of Advanced Technology, Department of Physics, Bar-Ilan University, Ramat-Gan 52900, Israel*

^b*Department of Electrical and Computer Engineering, Ben-Gurion University of the Negev, P.O.B. 653, Beer-Sheva, 84105 Israel*

Abstract

We study paramagnetic - ferromagnetic transition due to exchange interaction between classical localized magnetic moments and conduction electrons. By solving the Dynamical Mean Field Approximation equations we find explicit formula for the transition temperature T_c for arbitrary electron dispersion law, concentration and relation between exchange coupling and the electron band width. We present the results of calculations of the T_c for the semi-circular electron density of states.

Key words: , strong correlations, double-exchange model, magnetism, ferromagnetic order
PACS: 75.10.Hk, 75.30.Mb, 75.30.Vn

The double-exchange (DE) model [1,2,3] is one of the basic ones in the theory of magnetism. Magnetic ordering appears in this model due to exchange coupling between the core spins and the conduction electrons. The Hamiltonian of the model is

$$H = \sum_{nn'} t_{n-n'} c_{n\alpha}^\dagger c_{n'\alpha} - J \sum_{n\alpha\beta} \mathbf{S}_n \cdot \sigma_{\alpha\beta} c_{n\alpha}^\dagger c_{n\beta}, \quad (1)$$

where c and $c^\dagger$ are the electrons annihilation and creation operators, $\mathbf{S}_n$ is the operator of a core spin, $t_{n-n'}$ is the electron hopping, J is the exchange coupling between a core spin and n electrons, $\hat{\sigma}$ is the vector of the Pauli matrices, and α, β are spin indices.

We calculate the temperature of a paramagnetic-ferromagnetic transition T_c in a double-exchange model for arbitrary electron dispersion law, concentration and relation between the exchange coupling and the electron band width by formulating and solving the DMFA equations. We treat the core spins as clas-

sical vectors. The DE Hamiltonian in a single electron representation can be presented as

$$H_{nn'} = t_{n-n'} - J \mathbf{m}_n \cdot \sigma \delta_{nn'}. \quad (2)$$

Let us introduce Green's function and local Green's function

$$\hat{G}(E) = (E - H)^{-1}, \quad \hat{G}_{\text{loc}}(E) = \langle \hat{G}_{nn}(E) \rangle. \quad (3)$$

In the last equation, the averaging is with respect to random configurations of the core spins. In the framework of the DMFA approach to the problem (see [4] and references therein) the local Green's function is expressed through the the local self-energy $\hat{\Sigma}$ by the equation

$$\hat{G}_{\text{loc}}(E) = g_0 \left(E - \hat{\Sigma}(E) \right), \quad (4)$$

where $g_0(E) = \frac{1}{N} \sum_{\mathbf{k}} (E - t_{\mathbf{k}})^{-1}$ is the bare (in the absence of the exchange interaction) local Green's function. The self-energy satisfies equation

$$\hat{G}_{\text{loc}}(E) = \left\langle \frac{1}{\hat{G}_{\text{loc}}^{-1}(E) + \hat{\Sigma}(E) + J \mathbf{m} \cdot \hat{\sigma}} \right\rangle, \quad (5)$$

* Corresponding author. Tel: +972 8 6461583 fax: +972 8 6472949

Email addresses: kogan@quantum.ph.biu.ac.il (Eugene Kogan), marka@ee.bgu.ac.il (Mark Auslender).

where $\langle X(\mathbf{m}) \rangle \equiv \int X(\mathbf{m})P(\mathbf{m})$, and $P(\mathbf{m})$ is a probability of a given spin orientation (one-site probability). The quantities $\hat{G}$ and $\hat{\Sigma}$ are 2×2 matrices in spin space.

The DMFA assumption for the probability $P(\mathbf{m})$ is based on the Equation

$$\Delta D(E, \mathbf{m}) = -\frac{1}{\pi} \text{Im} \ln \det \left[1 + \left(J\mathbf{m}\hat{\sigma} + \hat{\Sigma} \right) \hat{G}_{\text{loc}} \right], \quad (6)$$

where the argument of both G_{loc} and Σ is $E + i0$. So the change in thermodynamic potential is [6,5,7]

$$\Delta\Omega(\mathbf{m}) = \int f(E) \Delta D(E, \mathbf{m}) dE, \quad (7)$$

where $f(E)$ is the Fermi function. The DMFA approximation for the one-site probability $P(\mathbf{m})$ is:

$$P(\mathbf{m}) \propto \exp[-\beta\Delta\Omega(\mathbf{m})]. \quad (8)$$

Eqs. (5) and (8) are the system of non-linear (integral) equations. In the ferromagnetic (FM) phase near the Curie temperature, Eqs. (5) and (8) can be linearized [5] with respect to $\mathbf{M}$. Thus we reduce the DMFA equations to a traditional MF equation [7]

$$P(\mathbf{m}) \propto \exp(-3\beta T_c \mathbf{M} \cdot \mathbf{m}). \quad (9)$$

The parameter T_c is formally introduced as a coefficient in the expansion of $\Delta\Omega(\mathbf{m})$ with respect to $\mathbf{M}$. Non-trivial solution of the MF equation $\mathbf{M} = \langle \mathbf{m} \rangle$ can exist only for $T < T_c$, hence T_c is the ferromagnetic transition temperature.

For the T_c , after straightforward, though lengthy algebra, we obtain

$$T_c = \frac{2J^2}{3\pi} \int_{-\infty}^{\mu} \text{Im} \left[\frac{g}{\frac{(\Sigma g' - g)(1 + \Sigma g)}{g' + g^2} - \frac{2J^2 g}{3}} \right] dE, \quad (10)$$

where Σ and g are determined by the properties of the system in the PM phase ($P(\mathbf{m}) = \text{const}$). Eq. (10) is the main result of our paper. Let us apply Eq. (10) to the case of semi-circular bare density of states $N_0(\varepsilon) = (2/W)\sqrt{E^2/W^2 - 1}$, for which Eq. (10) takes the form

$$T_c = \text{Im} \int_{-\infty}^{\mu} \frac{\frac{J^2 W^2}{6\pi} g^2 dE}{\left(E - \frac{W^2 g}{4}\right) \left(E - \frac{W^2 g}{2}\right) - \frac{J^2 W^2 g^2}{6}}. \quad (11)$$

For arbitrary exchange, the integral in Eq. (11) can be calculated only numerically. Note that that our main result (equation for the T_c) indicates it's own limits of validity. In part of the $J/W - n$ plane, Eq. (11) gives $T_c < 0$. Negative value of T_c means, that at any temperature, including $T = 0$, the paramagnetic phase is stable with respect to appearance of small spontaneous magnetic moment, and strongly suggests that the ground state in this part of the phase plane is non-ferromagnetic (NFM) [8].




Fig. 1. T_c as a function of electron concentration n : $J/W = .25$ (dotted line), $J/W = 1$ (dash-dotted line), $J/W = 2$ (dashed line), and $J/W = 20$ (solid line)




Fig. 2. The curve $T_c = 0$ on the $J/W - n$ plane

References

- [1] C. Zener, Phys. Rev. **82**, 403 (1951).
- [2] P. W. Anderson and H. Hasegawa, Phys. Rev. **100**, 675 (1955).
- [3] P. G. De Gennes, Phys. Rev. **118**, 141 (1960).
- [4] A. Georges, G. Kotliar, W. Krauth, and M. J. Rozenberg, Rev. Mod. Phys. **68**, 13 (1996). and S. Mahanti (Plenum Publishing, New York, 1999).
- [5] A. Chattopadhyay and A. J. Millis Phys. Rev. B **64**, 024424 (2001); A. Chattopadhyay, S. Das Sarma, and A. J. Millis Phys. Rev. Lett. **87**, 227202 (2001).
- [6] S. Doniach and E. H. Sondheimer, *Green's functions for solid state physicists* (Imperial College Press, London, 1998).
- [7] E. Kogan and M. Auslender, Phys. Rev. B **67**, 132410 (2003).

- [8] A. Chattopadhyay, A. J. Millis, and S. Das Sarma Phys. Rev. B **64**, 012416 (2001).